

## Claims

1. A tire puncture sealant comprising  
a latex of natural rubber,  
an emulsion of a tackifier and  
an antifreezing agent, wherein  
said tackifier is an aromatic modified terpene resin, and  
with respect to a total A+B+C of the solid content A of  
the natural rubber latex, the solid content B of the tackifier  
emulsion and the content C of the antifreezing agent which is 100  
weight %,   
the solid content A of the natural rubber latex is in a range of  
from 30 to 60 weight %,   
the solid content B of the tackifier emulsion is in a range of  
from 10 to 30 weight %, and   
the content C of the antifreezing agent is in a range of from 20  
to 50 weight %.
2. A tire puncture sealant according to claim 1, wherein  
said antifreezing agent is ethylene glycol and/or  
propylene glycol.